

A large white yacht with multiple decks and windows is shown sailing on a blue sea under a clear sky. The yacht is viewed from a side-on perspective, moving towards the right.

Thermal and acoustic foam insulation

Intek[®] PFI-1110

Intek[®] is a range of light weight high performance thermal and acoustic insulation products. Intek[®] emits virtually no smoke or incapacitating toxic biproducts when exposed to open flames. Intek[®] is lightweight, has a wide operating temperature range and can easily be removed for maintenance and then reused.

Intek[®] PFI-1110 is used in marine, commercial, industrial and defense markets as lightweight, non-flammable, thermal and acoustic insulation. It can be cut into a variety of shapes and sizes, and specialty facings are available to meet performance and specification requirements.

Intek[®] PFI-1110 is an ultra light weight Polyimide foam (6,4kgm³).

Benefits:

- Superior fire resistance - emits virtually no smoke or incapacitating toxic bi-products when exposed to an open flame and remains stable in high humidity
- Extremely lightweight - translating into fuel savings and efficiency
- Acoustic and thermal insulation - provides excellent acoustic absorption and thermal insulation properties
- Easy installation - lightweight, easy to cut and fit, and readily adapt to fabrication with other materials


Applications:

- Marine hull board
- Deckheads and bulkheads
- Hangar deck
- Beam and duct wrap
- HVAC duct liner
- Walls, roof and floor insulation in rail carriages
- Joints and pipe shoes for cryogenic pipelines at chemical facilities
- Electronic, medical and analytical instruments

Certificates*

- Defence Standard 07-247 Smoke and Toxicity
- BS 476 Part 6 Fire Propagation
- BS 476 Part 7 Surface Spread of Flame
- ISO 4589 - 2 Oxygen Index
- Fire-Restricting Materials per the International Maritime Organization (IMO) High Speed Craft code in accordance with ISO 9705 with IMO Res. MSC.40(64)
- ASTM C 1482

*Intek® PFI-1110 may meet additional specifications that are not listed here. Please contact us to determine if it meets your specification, or other requirements.



Classified as A1 by UK MOD meaning can be used in unlimited quantities on specific vessels and platforms

Typical Technical Data

Properties	Values	Testing
Density	0.40 (6.4)lb/ft ³ (kg/m ³)	ASTM D3574 Test A, ISO 845
Flame spread index	< 5	ASTM E84
Smoke developed index	< 5	ASTM E84
Limiting oxygen index	> 28%	ASTM D2863, ISO 4589-2: 1999
Noise reduction coefficient (NRC), 1 in (25 mm)	0.7	ASTM C423 and E795, Mounting A
Max continuous use temperature	400 (200)°F (°C)	
Thermal conductivity at 75° F (24°C)	0.32 (0.046)BTU-in/hr-ft ² -°F (W/mK)	ASTM C518
Max continuous use temperature	1.2 (8.3)lb/in ² (kPa)	ASTM D3574, Test C

The above are typical values subject to normal manufacturing variation.

Acoustical

Acoustical absorption coefficients (sabins/ft ² or metric sabins/m ²) ASTM C 423 and E 795, type A Mounting								
Thickness		Frequency (Hz)						
		125	250	500	1000	2000	4000	NRC
25mm	1 in	0.14	0.25	0.51	0.85	0.93	0.68	0.65
50mm	2 in	0.35	0.46	0.77	1.02	0.87	0.79	0.80

The above are typical values subject to normal manufacturing variation.

Trelleborg is an authorized distributor and fabricator of SOLIMIDE® Foams from Boyd Corporation.



Contact us

Trelleborg's Applied Technologies division is an industry expert in delivering innovative and reliable solutions that maximize performance for our customers. Our vast range of specialized, customizable materials ensure peace of mind at every stage of your project. With reliable and efficient project management and manufacturing we endeavor to take performance to new levels by achieving your goals safely, on time and within scope.



United Kingdom: +44 (0)1777 712500



Email: appliedtechnologies@trelleborg.com



TRELLEBORG

WWW.TRELLEBORG.COM/APPLIED-TECHNOLOGIES