



# TRELLEBORG

Engineered Coated Fabrics

## Polychloroprene Belt: RL 6765

### **Product Description:**

Trelleborg Style RL 6765 is a lightweight material designed for applications where its superb heat and flame resistance provide an extra margin of protection for people and equipment. It is a self-extinguishing material, ozone and weather resistant and can be used against caustics, gasoline, oil, water and steam.

### **Applications:**

Aircraft Firewall Barriers, Protective Sleeves, Tadpole Tape Covers, Flat Seals, Gaskets, Mounts and Door Seals.

### **Rubber Polymer:**

Polychloroprene

### **Finished Belt Requirement**

Color	Black
Thickness, inches	0.125" [+/- 0.015"]
Width, inches	Any width up to 58"
Weight, Pounds/Square yard	10.0 [+/- 1 lb/sqyd]
Operating Temperature, Fahrenheit	-40 to 200°
Mullen Burst, Minimum PSI	500

### **Rubber Compound Requirements**

Specific Gravity, g/cm <sup>3</sup>	1.60 [+/- 0.03]	ASTM D-297
Hardness, Durometer Shore 'A' or Equivalent	60 [+/- 5]	ASTM D-2240
Tensile Strength, Minimum PSI	1700	ASTM D-412
Elongation, Minimum	400%	ASTM D-412

### **Textile Requirements**

Reinforcement Fabric	Plain Weave Fiberglass
Tensile Strength, Minimum lbs/inch [Warp]	300
Tensile Strength, Minimum lbs/inch [Weft]	200

### **Quality Control**

Certifications and test results provided with the product at the time of shipment.

DATA SHEET: 13771 REV. B DATE: 10/11/13

\*All values are nominal unless otherwise specified.

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.