

Coating Innovations

Urethane (AU, EU)

Your Partner for Engineered Coated Fabrics

Trelleborg's engineered coated fabrics operation works with an outstandingly comprehensive variety of polymers, including AU/EU.

General Properties: Good aging and excellent abrasion, tear, and solvent resistance. Poor high temperature properties.

Resistant to: Ozone, hydrocarbons, moderate chemicals, fats, oils, greases.

Attacked by: Concentrated acids & alkali, ketones, esters, hot water & steam, chlorinated and nitro hydrocarbons.

General Polymer Characteristics:

Abrasion Resistance	Excellent
Compression Set	Fair
Elongation	Good
Flame Resistance	Poor
Gas Permeability	Good
Low Temp. Flexibility	Excellent
Tear Resistance	Excellent

Recommended Shelf Life

The recommended shelf life may vary based on polymer type and compound formulation. The actual life could vary dramatically based on storage conditions.

** This data is based on tests believed to be reliable and consistent with industry practices and is presented in good faith. No warranty or representation including but not limited to merchantability or of fitness for use whether expressed or implied is intended or made, nor is protection from law or patent to be inferred. Excellent, good, fair and poor are intended to serve as general guidelines only. Actual testing in the application environment is always recommended. All rights and patents reserved.*

Contact Us

Throughout the world, within the most technologically advanced industries, Trelleborg adds layers of innovation to ensure the highest performance in engineered coated fabrics.

Our polymer-engineered solutions are built on technical and industry know-how, delivered by experienced teams across a proven and efficient process methodology.



Our experts will help you find the optimum coating for your application requirements, using a proven formulation or a unique customized coating developed by our in-house development team.

USA; North Carolina:
+1 828-394-5120

Sweden: +46 410 510 00

Italy: +39 0371 4061

USA; Connecticut:
+1 203-468-0342

China: +86 21 51313188

Email: ECF@Trelleborg.com

www.TrelleborgECF.com